



PHYSICAL CHARACTERISTICS

| Sheens: | Gloss, Satin & Semi-Gloss |
|--------------------|-----------------------------|
| Color: | Amber |
| Solids: | 38-42% |
| VOC Content: | 550 VOC |
| Odor: | Solvent Like |
| Gloss Level (60%): | Minimum 90 GU for Gloss |
| | 60 - 65 GU for Semi Gloss |
| | 38 - 43 GU for Satin |
| | 20 - 24 GU for Matte |
| Stability: | 18 Months |
| Packaging Size: | 5-Gallon, 1-Gallon & Quarts |

APPLICATION CHARACTERISTICS

| Dry Color Clarity: Coverage Rate: | |
|---------------------------------------|---------------------------------------|
| Dry Time: | 3-4 Hours |
| Fully Cured: | .14 days |
| Leveling: | Very Good |
| Defoaming: | Excellent |
| Working Temp: | Room Temperature 65 – 75° F |
| Application Methods: | T-bar Applicator, Brush, or Roller |
| Storage Temp: Professional Market: | |

POLY-U-VAR PREMIUM URETHANE CLEAR WOOD FINISH

OVERVIEW: Superior Results for the Toughest Floors

Sampson Poly-U-Var Premium Urethane is an extremely durable varnish recommended for interior residential or commercial floors, paneling, cabinets, doors, trim, furniture, bar tops, etc. It is superior to conventional urethanes in toughness, resistance to abrasion and resistance to water and chemicals such as cleaners.

FEATURES

- High Build
- Exceptional Flow and Leveling
- Superior Abrasion Resistance

BENEFITS

- Low Odor
- Great for Interior Residential or Commercial Floors
- Available in 550 VOC Formulation



1999 Elizabeth Street • North Brunswick, NJ 08902 OFFICE (732) 821-3200 | FAX (732) 821-8180 **CANLAKCOATINGS.COM**